

Contite® PUE200/201



A POLYURETHANE RESIN FOR ELASTIC SEALING OF BOTH DRY & WET CRACKS

DESCRIPTION

Contite PUE200/201 is a two component, solvent and phthalate free, polyurethane system consisting of a resin component **Contite PUE200** and special hardener **Contite PU201**.

The system is ideal for the elastic sealing of cracks in concrete structures as well as areas suffering from water leakage.

USES & ADVANTAGES

Contite PUE200/201 can be used directly into dry & moist cracks, if water leakage must be stopped first.

Contite PUE200/201 can be used in combination with **Contite PUE100/E101** which will first stop the water and or react the water away after which the injection of **Contite PUE200/201** can be carried out.

Typical areas of use are :-

- The elastic sealing of cracks in concrete structures such as basements, tunnels etc.
- The sealing of cracks and joints and leaks in other structures.
- As injection material for injection hoses.

Advantages:-

- Good adhesion on wet as well as on dry concrete.
- Low viscosity, therefore a good penetration into the crack.
- Can be applied as one or as two component.
- The curing time can be adjusted relatively simply.
- The cured material is resistant to hydrolysis.
- Cracks can be injected with water before sealing. The advantage is adequate cleaning and a good control of the flow characteristics.

PROPERTIES

	Contite PUE200	Contite PU201
Colour :	yellow	dark brown
SG :	1.04-1.06	1.22-1.24
Viscosity at 25°C, mPa.s :	30-60	170-270
(at 77°F, lb/ft.s	0.02-0.04	0.11-0.18)
Pot life at 25°C (77°F) :	60-70 min.	
Gel time at 25°C (77°F) :	70-90 min.	

APPLICATION

Although **Contite PUE200/201** is a two component systems it can be used as a one component.

Used as One Component System

Step 1 : Add the required amount of **Contite PU201** to the **Contite PUE200**.

Step 2 : Mix it thoroughly until a homogeneous mixture has been obtained, which will be the case after about 2 minutes.

Step 3 : The mix can be pumped by means of a single component injection pump. Keep in mind that the gel time of the system is 70-90 minutes at 25°C (77°F).

After the injection the pump should be cleaned with **Contite PU Purge** (these product may not contain any water).

In the case of a two component application it is possible to speed up the reacting time to obtain faster curing. For this purpose Cormix supplies a special catalyst, **Contite Cat42**, to be added to the **Contite PUE200**.

The following table clearly indicates the influence of adding **Contite Cat42** to the **Contite PUE200** on the gel time of the mixture.

Dosage of Contite Cat42 in % by weight of Contite PUE200	Material Temperature		
	5°C (41°F)	21°C (70°F)	30°C (86°F)
	Reaction Time		
0%	~ 90 min	~ 90 min	~ 80 min
0.20%	~ 45 min	~ 40 min	~ 29 min
0.40%	~ 35 min	~ 30 min	~ 18 min
0.60%	~ 25 min	~ 25 min	~ 12 min
0.80%	~ 16 min	~ 15 min	~ 9 min
1.00%	~ 12 min	~ 11 min	~ 6 min

Note : The given data are laboratory parameters and may deviate depending on the object and conditions on site.

* To prevent condensation on the liquids at the start of work, the temperature of the components should be at least as high as the ambient temperature.

** All opened drums of **Contite PUE200/201** should be purged with dry nitrogen and capped when not in use.

MIXRATIO

Contite PUE200 : **Contite PU201** = 5 : 3 by weight or

Contite PUE200 : **Contite PU201** = 2 : 1 by volume

MECHANICAL & PHYSICAL PROPERTIES OF THE END PRODUCT

	According to	Unit	Value
Tensile strength :	ASTM D638	N/mm ²	2.0-2.1
		(psi)	290-305)
Elongation at break :	ASTM D638	%	60-80
Shore hardness :	ASTM D2240		20-30 D

Contite® PUE200/201



A POLYURETHANE RESIN FOR ELASTIC SEALING OF BOTH DRY & WET CRACKS

PACKAGING

16 kg (35 lb) set; **Contite PUE200** 10 kg (22 lb) & **Contite PU201** 6 kg (13 lb) in a can.

Other packing units on request.

STORAGE & SHELF LIFE

Contite PUE200/201 are very stable when properly handled.

To avoid problems, it is very important to understand that these materials are both temperature and moisture sensitive. Therefore, materials should be stored in an area with temperatures not exceeding 35°C (95°F) or not lower than 5°C (41°F), the shelf life is approximately 12 months in unopened drums.

All part used drums should be covered by nitrogen and re-sealed to prevent the ingress of moisture.

HEALTH & SAFETY

Ordinary hygienic principles, such as washing the compounds from the hands before eating or smoking should be observed. Hands should be washed with a waterless cleaner followed by soap and water. Avoid breathing of vapours, prolonged contact with the skin, contact with open breaks in the skin, and ingestion. Use **Contite PUE200/201** with adequate ventilation.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,

89 Romklat Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.