

Contite® PUE300/301



A POLYURETHANE RESIN FOR RIGID STRUCTURAL SEALING OF BOTH DRY & WET CRACKS

DESCRIPTION

Contite PUE300/301 is a two component, solvent and phthalate free, polyurethane system consisting of a resin component **Contite PUE300** and special hardener **Contite PU301**.

This system is ideal for the structural sealing of cracks in concrete structures as well as areas suffering from water leakage.

USES & ADVANTAGES

Contite PUE300/301 is applied directly into dry & moist cracks. If water leakage has to be stopped **Contite PUE300/301** can be used in combination with the **Contite PUE100/E101**. **Contite PUE100/E101** will first stop the water and/or react the water away, after which the injection of **Contite PUE300/301** can be carried out.

Typical areas of use are :-

- The structural sealing of cracks in concrete structures such as basements, tunnels etc. In areas where moist or wet cracks are present and a structural sealing is needed.

Advantages include:-

- Good adhesion on wet as well as dry concrete.
- Low viscosity; therefore good penetration into the crack.
- Can be applied as one or two component material.
- The curing time can be adjusted relatively simply.
- The cured material is resistant to hydrolysis.
- Cracks can be injected with water before sealing. The advantage is adequate cleaning and a good control of the flow characteristics.

PROPERTIES

	Contite PUE300	Contite PU301
Colour :	high yellow	dark brown
SG :	1.04-1.06	1.22-1.24
Viscosity at 25°C, mPa.s:	70-120	170-270
(at 77°F, lb/ft.s	0.047-0.08	0.11-0.18)
Pot life at 25°C (77°F) :	40-60 min.	
Gel life at 25°C (77°F) :	60-80 min.	

APPLICATION

Although **Contite PUE300/301** is a two component system it can be used as a one component system.

Used as One Component System

Step 1 : Add the required amount of **Contite PU301** to the **Contite PUE300**.

Step 2 : Mix it thoroughly until a homogeneous mixture has been obtained, about 2 minutes.

Step 3 : The mix can be pumped by means of a single component injection pump. The pot life of the system is 70-90 minutes at 25°C (77°F).

After the injection the pump should be cleaned with **Contite PU Purge**.

Used as Two Component System

In case a faster curing must be obtained **Contite PUE300/301** can be applied as a two component system by means of mixing / metering equipment. Due to the low viscosity of the components a simple static mixer can be used.

In the case of a two component application it is possible to speed up the reacting time to obtain faster curing. For this purpose Cormix supplies a special catalyst, **Contite Cat42**, to be added to the **Contite PUE300**.

The following table clearly indicates the influence of adding **Contite Cat42** to the **Contite PUE300** on the gel time of the mixture.

Dosage of Contite Cat42 in % by weight of Contite PUE300	Material Temperature		
	5°C (41°F)	21°C (70°F)	30°C (86°F)
	Reaction Time		
0%	~ 62 min	~ 60 min	~ 50 min
0.20%	~ 28 min	~ 27 min	~ 12 min
0.40%	~ 22 min	~ 20 min	~ 10 min
0.60%	~ 12 min	~ 11 min	~ 6 min
0.80%	~ 11 min	~ 8 min	~ 5 min
1.00%	~ 10 min	~ 7 min	~ 3 min

Note : The given data are laboratory parameters and may deviate depending on the object and conditions on site.

After injection the pumps and the mixing head should be cleaned with **Contite PU Purge**.

Note : To prevent condensation on the liquids at the start of work, the temperature of the components should be at least as high as the ambient temperature.

All opened drums of **Contite PUE300/301** should be purged with dry nitrogen and capped when not in use.

MIXRATIO

Contite PUE300 : **Contite PU301** = 1 : 1.15 by weight or

Contite PUE300 : **Contite PU301** = 1 : 1 by volume

Contite® PUE300/301



A POLYURETHANE RESIN FOR RIGID STRUCTURAL SEALING OF BOTH DRY & WET CRACKS

MECHANICAL & PHYSICAL PROPERTIES OF THE END PRODUCT

Tensile strength , N/mm ²	>50 (7,252 psi)
ASTM D638	
Compressive strength , N/mm ²	3 days >35 (5,076 psi)
ASTM D695	7 days > 50 (7,252 psi)
Elongation at break , %	4
ASTM D638	
Shore hardness :	75-80 D
ASTM D2240	

PACKAGING

18.70 kg (41.22 lb) set; **Contite PUE300** 8.70 kg (19.18 lb) & **Contite PU301** 10 kg (22.04 lb) in a can.
Other packing units on request.

STORAGE & SHELF LIFE

Contite PUE300/301 are very stable when properly handled.

To avoid problems, it is very important to understand that these materials are both temperature and moisture sensitive. Therefore, materials should be stored in an area with temperatures not exceeding 35°C (95°F) or not lower than 5°C (41°F), the shelf life is approximately 12 months in unopened drums.

All part used drums should be covered by nitrogen and re-sealed to prevent the ingress of moisture.

HEALTH & SAFETY

Ordinary hygienic principles, such as washing the compounds from the hands before eating or smoking should be observed. Hands should be washed with a waterless cleaner followed by soap and water. Avoid breathing of vapours, prolonged contact with the skin, contact with open breaks in the skin, and ingestion. Use **Contite PUE300/301** with adequate ventilation.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romkiao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.