

A 2 COMPONENT EPOXY RESIN PATCHING MORTAR

DESCRIPTION

A solvent free 2 part epoxy resin thixotropic patching mortar consisting of a resin and hardener containing especially selected fillers. On mixing a multifunctional epoxy adhesive & repair mortar is produced.

USES & ADVANTAGES

Condur 41 is an easy to apply epoxy mortar with medium size fillers allowing for various uses, these include :- repair of precast elements, finishing of I beam ends, repairing damaged concrete edges, providing an abrasion resistant lining, vertical & overhead repairs, also use as an adhesive.

Advantages include:-

- Easy to apply to precast elements & edges of concrete.
- Good build.
- Excellent adhesion.
- Abrasion & impact resistance.
- Excellent strengths.
- Suitable for both dry & damp surfaces.
- Unaffected by high humidity.
- Coloured components to ensure good mixing.
- Good chemical resistance.

PROPERTIES

Colour: Part A - White / Part B - Black

Density: Approx. 1.9-2.1 kg/litre

Mixing ratio: Part A : B = 2 : 1 by weight
Part A : B = 2 : 1 by volume

Pot Life: **Temperature °C 6 kg set**

40	30-40 min.
30	60 min.
20	90 min.

Note: To obtain maximum pot life, spread **Condur 41** into a thin (less than 10 mm.) layer immediately after mixing.

Compressive strength: 1 Day 60-64 N/mm²

ASTM D695 7 Days 70-75 N/mm²

28 Day 78-82 N/mm²

Flexural Strength: 25-35 N/mm² at 28 days

Bond Strength: >13 N/mm² at 28 days

ASTM C882

Data quoted is typical for this product and does not constitute a specification.

Note: To obtain performance characteristics stated in this data sheet, the mixing ratio must be maintained.

SURFACE PREPARATION

All grease, oil, chemical contamination, dust, laitance and loose concrete must be removed by scabbling or light bush hammering to provide a sound substrate. Concrete must be at least 14 days old prior to treatment. Steel surfaces should be grit blasted to white metal. Surfaces which show any traces of oil must be degreased with a chemical degreaser prior to grit blasting.

PRIMING

Surfaces to receive **Condur 41** should be well primed with **Condur EA2** first.

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.

MIXING

Care should be taken to ensure that **Condur 41** is mixed thoroughly. The hardener and the resin components should first be stirred separately to disperse any settlement. The entire contents of the hardener tin should then be poured into the resin tin and the two components mixed thoroughly using a low-speed drill and paddle for at least 2 minutes until a uniform colour is obtained.

APPLICATION

Apply the mixed **Condur 41** with a notched trowel, putty knife, caulking gun, etc. depending upon the application. Bonded surfaces should be held rigidly together until the **Condur 41** has set.

COVERAGE RATES

Approx. 2 kgs/m² /mm thickness.

CLEANING

Clean all tools immediately after use with thinner.

PACKAGING

6 kg set (A+B).

STORAGE & SHELF LIFE

Condur 41 has a shelf life of 12 months when stored in a dry place below 35°C in unopened containers.

HEALTH & SAFETY

Prolonged and repeated skin contact with epoxy resins and curing agents may cause dermatitis in persons sensitive to these products. Gloves, barrier creams, protective clothing and eye protection should be worn when handling these products. If poisoning occurs, contact a doctor or Poisons Information Centre. If swallowed, do **NOT** induce vomiting-give a glass of water. If in eyes, hold eyes open, flood with water for at least 15 minutes. If skin contact occurs, remove contaminated clothing and wash skin thoroughly.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

http://www.cormix.com E-mail : info@cormix.com