

2 COMPONENT EPOXY RESIN BONDING AGENT FOR BONDING WET CONCRETE TO EXISTING CONCRETE

DESCRIPTION

A two component solvent free epoxy bonding agent. The base component is white and the hardener component is black providing visual evidence of adequate mixing. Conforms to ASTM C881-78 Type II Grade 2 Class B & C.

USES & ADVANTAGES

Condur EA2 is used for bonding fresh wet cementitious materials to existing cementitious surfaces. Typical uses include structural bonding of new to existing concrete and as a bonding agent on concrete, mortar, steel and iron etc. It is ideally suited for roads, bridges, pavements, loading bays and factories. **Condur EA2** may also be used as part of a repair system or a repair barrier in permanently wet or damp areas.

Advantages include:-

- Can be applied on to dry or damp substrates.
- Solvent free.
- Long pot life therefore suitable where formwork or additional reinforcement has to be installed.
- Unaffected by moisture.
- Exhibits high mechanical strength.
- Easy to apply.
- Exceeds the tensile strength of the host concrete.

PROPERTIES

Appearance :	Base : White Hardener : Black
Pot life :	35 - 45 mins.
Specific gravity (mixed) :	Approx. 1.35 - 1.45
Initial hardness :	2 - 4 hours
Full cure :	7 days
Max.overlay time :	90 minutes.
Compressive strength :	> 80 N/mm ² at 7 days
Tensile strength :	25 N/mm ²
Flexural strength :	45 N/mm ²
Shear strength :	40 N/mm ²
Bond strength to concrete :	3 - 4 N/mm ² (concrete failure)
Bond strength to steel :	15 - 20 N/mm ²

Note: Properties measured at 20°C. Data quoted typical for this product does not constitute a specification. To obtain performance characteristics stated in this data sheet, the mixing ratio must be maintained.

SUBSTRATE PREPARATION

Clean the surface and remove any dust, unsound material, plaster, oil, paint, grease, corrosion deposits or algae. Roughen the surface and remove any laitance and expose aggregate by light scabbling or grit-blasting. Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or a proprietary degreaser. The effectiveness of decontamination and soundness of the substrate should then be assessed by a pull-off test.

MIXING

Any steel reinforcement and formwork should be prepared, cut to size and shape, and made ready for assembly before mixing commences. Care should be taken to ensure that **Condur EA2** is thoroughly mixed. The "hardener" and "base" components should be stirred separately before mixing to disperse any settlement. The entire contents of the "hardener" tin should then be poured into the "base" tin and the two materials thoroughly mixed using a suitable slow-

speed drill and mixing paddle for about 2 minutes until a fully uniform colour is obtained. The sides of the tin should then be scraped and mixing should continue for a further 2 minutes.

APPLICATION

Condur EA2 should be applied as soon as the mixing process has been completed. It should be brush or spray-applied to the prepared surfaces. On damp surfaces ensure that it is well brushed in. The new concrete or screed should be applied to the coated substrate within 90 minutes at 30°C.

At ambient temperatures above 30°C, the material should be stored in the shade or in an air-conditioned environment for 12 hours before use.

ESTIMATING

Condur EA2 4 - 5 m²/litre depending on the porosity and surface of substrate.

CLEANING

Clean all tools immediately after use with **Cormix Cleaner**. Hardened material can only be removed mechanically.

PACKAGING

6 kg pre-measured sets.

STORAGE & SHELF LIFE

Condur EA2 has a shelf life of 12 months if kept in a dry store in the original unopened packs. If stored at high temperatures, the shelf life may be reduced.

HEALTH & SAFETY

Ensure adequate ventilation and avoid inhalation of vapours. Wear suitable protective clothing, gloves and eye protection. Remove from skin immediately with resin removing cream and wash with soap and water. Do not use solvent. If poisoning occurs, contact a Doctor or Poisons Information Centre. If swallowed, do **NOT** induce vomiting give a glass of water. If in eyes, hold eyes open, flood with water for at least 15 minutes and see a doctor. If skin contact occurs, remove contaminated clothing and wash skin thoroughly.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romklao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

Rev. 010 : Jun 2010

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.