

3 COMPONENT POURABLE EPOXY GROUT

DESCRIPTION

A three component pourable epoxy grout based on high grade epoxy resin and specially graded aggregates. Mixes to a flowable grout. For use in heavy engineering and difficult conditions.

USES & ADVANTAGES

Condur EG is a high strength epoxy grout with no shrinkage, and is suitable for many grouting applications including bridge bearing plates, machine bases such as pumps, generators, motors, turbines, compressors etc., fixing bolts and anchors, crane rail tracks, reinforcement, and cavities in concrete etc.

Advantages include:-

- Chemical resistance.
- Solvent free.
- Shrinkage free hardening.
- Rapid hardening.
- High mechanical strength.
- Curing is not affected by high humidity.
- Good impact and vibration resistant.
- High adjustable flow.
- Good bonding to most substrates.
- Prepared ready to use.

TYPICAL PROPERTIES

Components:	3 (Base, hardener & Filler)
Form:	Pourable
Appearance:	Black (when mixed)
Mixed Density (kg/ltr):	2.22 ± 0.05
ASTM C905	
Working Time:	50 - 60 mins.
Compressive Strength:	1 day 55 N/mm ²
ASTM C579	3 days 68 N/mm ²
	7 days 80 N/mm ²
Flexural Strength:	7 days 35 N/mm ²
ASTM C580	
Tensile Strength:	7 days 25 N/mm ²
ASTM C307	
Bond Strength:	7 days > 2.5 N/mm ²
ASTM D4541	(Concrete Failure)

Chemical resistance (ASTM D543):

Citric Acid 10%	Excellent
Tartaric Acid 10%	Excellent
Acetic Acid 5%	Satisfactory
Nitric Acid 25%	Good
Hydrochloric Acid 25%	Excellent
Sulphuric Acid 50%	Very Good
Sodium Hydroxide 50%	Excellent
Diesel Fuel / Petrol	Very Good
Sugar Solutions	Very Good
Lactic Acid	Very Good
Hydrocarbons	Very Good
Phosphoric Acid 50%	Very Good

Application Temperature: +10°C to +40°C

Service Temperature: +5°C to +60°C

Note:

- The above data is typical under laboratory conditions at 25°C and does not constitute a specification. Field trials are recommended.
- The working time starts when the hardener is added to the resin material. Do not let the resin and hardener stand still without adding aggregates which may result in shorter working time. Working time will vary depending on the temperature and the quantity mixed. To get the optimum working time keep the material shaded and in a cool place.

SUBSTRATE PREPARATION

Foundation Preparation

- Concrete should be old enough, if it is newly placed concrete then it needs to be 21-28 days old and to have reached its design strength.
- Concrete should have attained a minimum compressive strength of 21 MPa, higher strength concrete is recommended for optimum performance of grout.
- All surfaces should be dry, clean, free from standing water, grease, curing compounds, mould oils, all loosely adhered aggregates and cement particles, etc.
- Chip the concrete surface so aggregates are exposed to ensure all laitance and weak particles are removed. Alternatively use a spray on surface retarder when placing concrete. The exposed aggregate amplitude should not be greater than 10-15 mm.

3 COMPONENT POURABLE EPOXY GROUT

- Chamfer the edges of the concrete 45 degrees to 50 mm. width to avoid sharp corners which helps to reduce the potential for cracking.
- If anchor bolt sleeves are to be placed, be sure all water is removed and the void completely dry.
- Shade the foundation from direct sunlight for at least 24 hrs before grouting and 48 hrs after grouting.

Equipment Preparation

- Ensure the surface of base plate to be bonded with grout is free from rust, coatings, wax, oil, grease or scale. Mechanical methods such as grinding, sanding, etc can be used to remove laitance, scale, etc to give a sound and clean surface.
- Primers can be used when there is a long delay in cleaning and grouting which could allow rusting and contamination of base plate.

Formwork Preparation

- Before placing the formwork ensure the foundation and equipment is protected from rain or moisture.
- Seal off the areas that will not be grouted.
- Place forms no greater than 50 to 100 mm away from the edge of individual base plate or sole plate. However this may vary depending on the site requirement and application.
- Excessive edges/shoulders, may create thermal stress resulting in cracks.
- For long and narrow placements create a headbox to maintain pressure and to enhance proper placement.
- Forms should be liquid tight, they should be sealed with sealant, putty, foam or caulk. Do not allow to contact the grout.
- For long pours it is recommended to install expansion joints or divide the sections not exceeding 1.1m in length. This reduces the opportunity for cracking due to the exothermic reaction of the material and differences in linear thermal expansion & contraction between the epoxy grout and concrete.

Deep Pour Recommendations

- Where ever a deep pour is necessary it is recommended to use rebar of 9 to 14 mm diameter to minimize stress cracking.

- Grouting should be done in multiple layers if more than the recommended thickness.
- When pouring in multiple layers ensure the previous layer is hardened and cooled.
- For deep pour applications pouring in a single layer with rebar installed, use **Condur EGLP**.

MIXING

- Before mixing ensure all the components are cool, shaded and dry. If not preconditioned store all components below 25°C for 24 hrs before using.
- The temperature of grout, baseplate and foundation are more important than the air temperature because they are directly related to the flow of grout.
- Add component A & B in a mixing vessel and mix under slow speed (RPM 400) for approximate 1 minute. Then add component C and continue mixing until a flowing uniform grout is achieved.
- Avoid excessive mixing which will result in reduction of working time and heat generation.

APPLICATION

- While grouting the base plates ensure there is sufficient pressure head to maintain movement of grout.
- Base plates with a flat base pour the grout from one side through the other across the short dimensions.
- Ensure entrapped air can escape when grouting closed areas.
- Where grout cannot flow or have smooth movement because of the length of pour pushing aids like steel chains, strips of plywood, etc can be used.
- The base plate with anchor bolts, dowel, starter bar, etc. should be grouted first followed by the base plate.
- If grouting in multiple layers, it is necessary to sprinkle a small amount of 2.5 mm aggregate over the first layer before the grout reaches its setting time. Before placement of 2nd layer brush out loose aggregates from the 1st pour. Another method is to scabble gently the top surface and make it rough when grout reaches near to its setting time.

3 COMPONENT POURABLE EPOXY GROUT

GROUTING THICKNESS

Minimum 10 mm to a maximum 70 mm in a single layer.

TYPICAL DETAIL




Figure 1 - Regular Equipment




Figure 2 - Engine with Oil Pan




Figure 3 - Rail or Soleplate




Figure 4 - Typical Rail with Expansion Joint Section




Figure 5 - Typical Epoxy Chock Application

Key

- | | |
|----------------------------|----------------------------|
| 1. Concrete Foundation | 6. Form |
| 2. Grout | 7. Soleplate or Rail |
| 3. Equipment Base | 8. Shim or Chock |
| 4. Anchor Bolt | 9. Expansion Joint |
| 5. Anchor Bolt Sleeve Seal | 10. Dowel or exposed rebar |

FINISHING

A smooth finish may be achieved before the grout reaches its setting time by spraying or brushing the surface with xylene, white spirit or epoxy grade thinner and then by using the steel trowel or wooden trowel level the surface.

CURING

- Cure time will depend on the ambient and substrate temperature. For the best results pour the grout and cure above 12°C.
- The grouts setting time will be delayed and will not achieve the desired properties at temperatures below 5°C.
- For cold weather grouting please contact CORMIX Technical Department for assistance.

IMPORTANT NOTES TO ACHIEVE PRODUCT PERFORMANCE

- Do not alter the ratio of resin and hardener. Fillers can be varied as per site requirement.
- Do not thin the grout with solvent or water to make it more flowable.
- Always use a headbox to maintain pressure and the grouts flowability.
- Epoxy based grouts sometimes develop cracks. Cracks are generally caused by thermal stresses, temperature difference, sharp corners and edges, etc. Horizontal edge cracks may occur just below the grout concrete interface especially in outdoor installations. Chamfering the concrete edge helps in reducing such cracks.
- To reduce/prevent curling use dowels or scabble back to expose rebar.
- Following proper installation procedures will reduce the amount of crack development. The procedures contained in this data sheet highlight generally accepted field practises for successful grouting. These may be followed, modified or rejected by the user, however, they are not Cormix responsible for planning & understanding the installation appropriate to the conditions. If planned procedures differ from the data sheet contact Cormix Technical Service Department.
- If cracks develop use **Condur SC** (Low viscosity epoxy resin system) to repair the cracks. Consult **Cormix**.
- Make certain the most current version of the TDS & MSDS are being used by contacting Cormix CS.
- Proper application is the responsibility of the user, field visits by Cormix personnel are for the purpose of making technical recommendations only & not for supervising or providing quality control at the job site.

3 COMPONENT POURABLE EPOXY GROUT

CLEANING

Clean all tools and equipment immediately with **Cormix Cleaner**.

PACKAGING

A+B+C 10&25 kg. pre-measured sets or larger packaging upon request.

HEALTH & SAFETY

Avoid contact with skin and eyes and avoid breathing vapour. Use only in well ventilated areas away from heat sparks or naked flame. Wear suitable protective clothing, gloves and eye protection when mixing or using. If poisoning occurs, contact a doctor or Poisons Information Centre. If swallowed, do **NOT** induce vomiting give a glass of water. If in eyes, hold eyes open, flush with water for at least 15 minutes and see a doctor. If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.

STORAGE & SHELF LIFE

Store in dry conditions between 5°C - 30°C. The shelf life is 12 months when unopened and stored correctly.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romklao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.