

## 2 COMPONENT EPOXY COATING FOR REBAR

### DESCRIPTION

A two component high build, high solids epoxy coating for rebar and maintenance work. Available in aluminium pigmented version to provide additional corrosive barrier protection.

### USES & ADVANTAGES

**Congard ST** is a surface tolerant product used in a wide variety of applications and for various substrates including hand prepared rusty steel, rebar, abrasive blast cleaned and hydroblasted steel, and over existing intact but aged coatings.

Areas of use include anti corrosive protection to steel and rebar in industrial, coastal structures, pulp and paper plants, bridges and offshore environments in both atmospheric exposure and immersion.

#### Advantages include:-

- High build.
- May use on hand prepared rebar & steel.
- May use with steel coating systems.
- High coverage rate : 6m<sup>2</sup>/litre
- Economical.
- Apply by brush, roller or spray.
- Small packaging for small jobs - low wastage.
- May use with Cormix repair systems.
- Two Part.
- Rapid drying.
- One coat application possible.

### PROPERTIES

**Appearance/Colour:** Aluminium  
**Gloss Level:** Eggshell  
**Volume Solids:** 80-85% (depends on colour)  
**Typical Thickness:** 100-200 microns (4-8 mils)  
 dry equivalent to 122-244 microns (4.9-9.8 mils) wet.  
**Theoretical Coverage:** 6.5 m<sup>2</sup>/litre at 125 microns d.f.t. and stated volume solids.  
**Practical Coverage:** Allow appropriate loss factors.  
**Method of Application:** Airless spray, air spray, brush, roller.

#### Drying Time:

Temp.	Touch Dry	Hard Dry	Overcoating Interval <b>Congard ST</b> with self		Overcoating Interval with Recommended topcoats	
			Min.	Max.	Min.	Max.
25°C	4 hrs.	16 hrs.	16 hrs.	14 days	8 hrs.	7 days
40°C	2 hrs.	6 hrs.	6 hrs.	7 days	4 hrs.	3 days

Flash Point	Base (Part A)	C/A (Part B)	Mixed
	36°C	31°C	35°C

### SUBSTRATE PREPARATION

The performance of this product will depend upon the degree of surface preparation. The surface to be coated should be clean, dry and free from contamination. Accumulated dirt and soluble salts must be removed. Dry bristle brushing will normally be adequate for accumulated dirt. Soluble salts should be removed by fresh water washing.

#### Abrasive Blast Cleaning

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

A surface profile of 50-75 microns (2-3 mils is recommended).

#### Hand or Power Tool Preparation

Note, all scale must be removed and areas which cannot be prepared adequately by chipping or needle gun should be spot blasted.

#### Aged Coating

**Congard ST** is suitable for overcoating a limited range of intact, tightly adherent coatings. Loose or flaking coatings should be removed back to a firm edge. Glossy finishes may require light abrasion to provide a physical "key".

### MIXING / APPLICATION

Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified

- (1) Agitate Base (Part A) with a power agitator.
- (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.

**Mix Ratio:** 5.67 part : 1.00 part by volume.

**Working Pot Life:** 25°C 40°C  
 2 hours 1 hour

#### Airless Spray:

Recommended - Tip range 0.45-0.58 mm. (18-23 thou)  
 - Total output fluid pressure at spray tip not less than 176 kg/cm<sup>2</sup> (2,500 p.s.i.)

#### Air Spray (Pressure Pot):

Recommended Gun De Vilbiss MBC or JGA  
 Air Cap 704 or 765  
 Fluid Tip E

#### Brush:

Recommended Typically 100-125 microns (4-5 mils) can be achieved.

#### Roller:

Recommended Typically 75-100 microns (3-4 mils) can be achieved.

**Thinner:** Cormix Thinner

**Cleaner:** Cormix Cleaner

## 2 COMPONENT EPOXY COATING FOR REBAR

### APPLICATION

Clean all equipment immediately after use with Congard Thinner. It is good working practice to periodically flush out spray equipment during the course of the working day. In order to achieve optimum performance on hand prepared steel, the aluminium pigmented version should be applied.

Maximum film build in one coat is best attained by airless spray. Application by air spray may require a multiple cross spray pattern to attain maximum film build. Low or high temperatures may require specific application techniques to achieve maximum film build. If salt water is used in the wet blast process the resulting surface must be thoroughly washed with fresh water before application of **Congard ST**.

**Congard ST** is suitable for overcoating intact, aged alkyd, epoxy and polyurethane systems. However, this product is not recommended where thermoplastic coating such as chlorinated rubbers and vinyl have previously been used. Please consult Cormix International for alternative recommendations.

Surface temperatures must always be a minimum of 3°C (5°F) above dew point.

Level of sheen and surface finish is dependent on application method. Avoid using a mixture of application methods whenever possible.

In common with all epoxies **Congard ST** will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

Premature exposure to ponding water will cause a colour change, especially in dark colours.

### PACKAGING

5 and 20 litre units in oversized cans for mixing.

For availability of other pack sizes contact Cormix International Limited.

### STORAGE & SHELF LIFE

12 months minimum at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

### HEALTH & SAFETY

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s). All work involving the application and use of this product should be performed in compliance with all relevant National, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult Cormix International Ltd. for further service.

### TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

### QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

### CONTACT DETAILS

#### Cormix International Limited

Regional Office,

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : [info@cormix.com](mailto:info@cormix.com)

**NOTE :** Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.