

POLYMER BONDING AID & WATERPROOFING ADMIXTURE

DESCRIPTION

Conmix Latex is an aqueous emulsion especially formulated for use with cementitious mixes. It is used in mortar and concrete to improve the waterproofing, wear resistance, durability and bonding properties. Mortars containing **Conmix Latex** may be used for vertical, horizontal and overhead repair work.

USES & ADVANTAGES

Conmix Latex is used to substantially improve the qualities of cement mixes, for example: thin layer patch mortars, renders, floor screeds, concrete repair mortar, abrasion resistant linings, fixing mortars, bonding slurry etc.

Advantages include:-

- Excellent water resistance.
- Increased durability.
- Plasticising effect and reduces shrinkage.
- Improved corrosion protection.
- Economical.
- Higher flexibility.
- Good resistance to many salts and chemicals.
- Excellent adhesion to concrete, mortar, stonework, plaster & blockboard.
- Thermal expansion and elastic modulus similar to concrete.
- Non toxic.
- Improves cohesion & workability.
- Single component easily gauged.
- Improved flexural & tensile properties allow for thin application.

PROPERTIES

The below results are approximated and achieved by considering the properties of a sand : cement mortar at 3 : 1 combined with **Conmix Latex** at 10 litres per 50 kg. of cement.

Appearance:	White Liquid
Specific Gravity:	Approx. 1.02 kg/litre
Compressive Strength:	50 - 75 N/mm ² BS 6319, Part 2 1983
Tensile Strength:	3 - 3.3 N/mm ² ASTM C-190-85
Flexural Strength:	8 - 9 N/mm ² BS 6319, Part 3 1983
Slant shear bond:	50 - 54 N/mm ² BS 6319, Part 4 1984

Chemical resistance:

Adding **Conmix Latex** to cement mortars reduces permeability and therefore helps reduce the rate of attack by aggressive chemicals, acid gases and water.

SUBSTRATE PREPARATION

Saw cut or cut back the extremities of the repair locations to a depth of at least 10 mm. to avoid feather-edging and to provide a square edge. Break out the complete repair area to minimum depth of 6 mm. up to the sawn edge.

REBAR PRIMING

Prime rebar with **Congard Zinc** or **Congard ST**.

MATERIALS

Aggregates and sand should be clean and well graded. Sand particle size should relate to applied thickness of mortars and required surface finish.

SUBSTRATE PRIMING

The substrate should be thoroughly soaked with clean water and any excess removed prior to commencement. A slurry primer should be prepared consisting of 1 volume **Conmix Latex** to 1 volume clean water to 1-3 volumes fresh cement. The slurry should be stirred frequently during use to offset settlement & worked well into the surface. Avoid ponding. The repair mortar, topping or render must be applied on the wet slurry primer. If the slurry primer dries before application of the mortar, it must be removed and the area reprimed before continuing.

MIXING

Hand mixing is not recommended. Preferably a forced action mixer or low speed drill with appropriate paddle should be used. Hand mixing should only be undertaken with small quantities. Weigh the cement, sand and, where required, aggregate into the mixer and dry blend together for one minute. With the machine in operation, add the pre-mixed **Conmix Latex** and clean water. Continue mixing for 3 minutes to ensure complete dispersal into the sand and cement. Make any small adjustment to the quantity of clean water but do not significantly exceed the dosage shown below. Mix until lump free with creamy consistency.

METHOD OF USE

In all situations the surface must be in a clean, laitance free and roughened state. Absorbent surfaces should be saturated thoroughly with water, but avoid ponding. Oil or grease deposits should be cleaned away. Pull off tests should be conducted to assess decontamination. Expose rebar & clean to bright condition. Grit or sand blast. Remove any corrosive agents such as chloride by high pressure water blasting.

APPLICATION

Conmix Latex mortars, toppings and renders must be well-compacted on to the primed substrate by trowel. Exposed steel reinforcement should be completely encapsulated by the mortar. **Conmix Latex** mortars can be applied at a minimum thickness of 6 mm. and up to 40 mm. thickness, dependent on the location and configuration of the repair zone. Where thick sections up to a total thickness of 40 mm. are to be built up by hand or trowel application, the surface of the intermediate layers should be scratch-keyed. Application of the slurry primer and a further application **Conmix Latex** mortar may proceed as soon as this layer has set.

POLYMER BONDING AID & WATERPROOFING ADMIXTURE

MIXDESIGN

Repair Mortar - Mix Design

Thickness : 6 mm. - 40 mm.

- 10 litre of **Conmix Latex**
- 8 litres of Clean water.
- 50 kgs. of Ordinary Portland Cement.
- 150 kgs. of Sand - fine to coarse depending on layer thickness.

Floor Screeds - Mix Design

Thickness : 10 mm. - 40 mm.

- 10 litres of **Conmix Latex**
- 6 litres of Clean water.
- 50 kgs. of Ordinary Portland Cement.
- 150 kgs. of sand - coarse sand up to 6 mm. depending on coat thickness.

The screed should be semi dry.

Renderers - Mix Design

Thickness : 6 mm. - 9 mm.

- 10 litres of **Conmix Latex**
- 6 litres of clean water.
- 50 kgs. of Ordinary Portland Cement.
- 150 kgs. of Fine sand.

The render should be semi dry & cohesive.

Bonding Coat for Rendering / Bonding between old & new concrete

Conmix Latex : Water - 1 : 1

Dry mix : Cement : Fine sand - 1 : 1 or cement only.

Mix as mixing instruction above.

Apply slurry to prewetted substrate in 1 - 2 mm. thickness & place new concrete or water immediately before the slurry dries. **Place Wet on Wet.**

The above mixes are based on dry sand & aggregate. Site conditions & varying moisture contents will effect final performance.

Dry mix cement, sand and aggregate (if needed) for at least 1 minute before adding the premixed **Conmix Latex** & water. Mix for at least another 5 minutes. Do not use excessive amounts of water. Allowance must be made for the water content in the sand.

CURING

Cure with **Corcure 180** or **Corcure 90**.

SUBSEQUENT FINISHES

Conmix Latex can be finished with a steel, plastic or wood float, or by a damp sponge technique, to achieve the desired surface texture. The completed surface should not be overworked.

PACKAGING

25 litre pails; 200 litre steel drums.

STORAGE & SHELF LIFE

Conmix Latex should be stored protected from sunlight and frost. The shelf life is at least 6 months in original unopened containers.

HEALTH & SAFETY

Wear suitable protective clothing, gloves and eye protection. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. If poisoning occurs, contact a doctor or Poisons Information Centre. If swallowed, **DO NOT** induce vomiting - give a glass of water. If in eyes, hold eyes open, flush with water for at least 15 minutes and see a doctor. If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romklat Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.