

Conpatch[®] 600



ONE PART POLYMER MODIFIED FINE CONCRETE REPAIR MORTAR

DESCRIPTION

A ready to use economical one component polymer modified repair mortar containing fibres and silica fume. **Conpatch 600** contains specially selected materials to provide a fine, smooth repair material.

USES & ADVANTAGES

Conpatch 600 is a fine, ready to use repair mortar for repairing concrete surfaces including small honeycombs, surface defects, blowholes and minor damage. It can also be used to repair corrosive damage to concrete surfaces.

Advantages include:-

- Easy to apply. Excellent workability.
- Non shrink. Non toxic. Non corrosive.
- Water & weatherproof.
- Reduces carbonation significantly.
- Excellent adhesion and mechanical strengths.
- Contains no chlorides or salts that may cause corrosion.
- Gives better control than two part systems.
- Provides cost saving over two part systems.
- Good colour matching to concrete.
- Non sagging.
- Good resistance to chlorides & sulphates.
- Contains fibres to reduce micro cracking and improve durability.

PROPERTIES

Appearance:	Grey powder
Compressive Strength:	50 - 65 N/mm ² after 28 days at 25°C
Flexural Strength:	12 - 15 N/mm ² after 28 days at 25°C
Bond Strength to Concrete:	1.75 - 3 N/mm ² after 28 days at 25°C
Drying Shrinkage:	<400 microstrain at 7 days <560 micron strain at 28 days
Coefficient of Thermal Expansion:	11 x 10 ⁻⁶ /°C
Water Absorption ISAT:	10 mms < 0.007 ml/m ² /sec
BS 1881 Part 5 1970:	2 hours < 0.0045 ml/m ² /sec

Note: Properties depend on water content.

SUBSTRATE PREPARATION

The substrate should be clean & sound. Remove dirt, dust, oil, grease, laitance, sealers, release agents, curing compounds & paints.

Exposed rebar should be cleaned & protected with **Congard Zinc**.

The concrete should be presaturated for preferably 6 hours with water before application.

PRIMING

Priming is not normally required. Surfaces to receive **Conpatch 600** should be well saturated with water first.

MIXING

Conpatch 600 is simply mixed with water to yield a stiff easily workable compound with shrinkage compensating properties.


The quantity of water depends on the desired consistency but as a guide we recommend 16-18% by weight of **Conpatch 600**.

Mix with a paddle mixer or trowel for at least 3 minutes to ensure a homogenous lump free material is achieved. Do not try to remix the product after losing workability by the addition of more water.

Typical Procedure for Concrete Repair Using Conpatch Repair Mortars




Remove damaged concrete and prepare exposed steel reinforcement.



Thoroughly clean area of repair using high pressure water jet to remove all loose debris and contamination. Fingers should be able to be fitted behind rebar.



Mix and apply **Congard Zinc** to rebar allow to dry. Apply **Conmix Latex** bonding bridge if required. Apply repair material WET ON WET to bonding bridge.




Replace damaged concrete using **Conpatch 600** one component polymer modified mortar, build up in layers if necessary.



Once set firm, the repair and surrounding area coat with **Corcure 90** or **Corcure 75** curing compound.



Remove any remaining **Corcure 90** from treated area if to overcoat.



Any further leveling may be achieved with fairing material.



A final coat of **Elastoclad** decorative elastomeric, anti-carbonation coating will prevent the ingress of water chlorides and other aggressive influences, effectively halting the carbonation process. **Elastoclad** is water vapour permeable, allowing the substrate to breathe, and has excellent elasticity, bridging dynamically moving cracks even at low temperatures.

Conpatch[®] 600



ONE PART POLYMER MODIFIED FINE CONCRETE REPAIR MORTAR

METHOD OF USE

Apply **Conpatch 600** with a trowel, spatula, float or by spray. By hand press hard. Work up to 20 mm. in one layer. Thicker repairs may be achieved by working in layers.

CURING

To prevent rapid surface drying and crazing, use a suitable curing compound from Cormix 's Corcure range e.g. **Corcure 90**.

CONSUMPTION

Approx. 2 kg/m²/mm.

PACKAGING

25 kg. 4 ply plastic lined bags.

STORAGE & SHELF LIFE

Conpatch 600 has a shelf-life of up to 12 months in unopened packs kept in a dry store. If high humidity is apparent the life may be reduced to 6-8 months.

HEALTH & SAFETY

Conpatch 600 is non-toxic but is alkaline in its nature. When applying gloves & goggles should be worn. Wash off splashes to skin with water. If in eyes wash out with plenty of clean water and seek medical attention. **Conpatch 600** is non-flammable.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,
89 Romkiao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.