

RAPID STRENGTH CEMENTITIOUS PRECISION GROUT / MORTAR

DESCRIPTION

Congrout RES is a rapid early strength non shrink cementitious grout/mortar. **Congrout RES** provides a flowing grout/mortar with controlled expansion in both wet and hardened states. It should be specified where rapid early strength gain is required.

USES & ADVANTAGES

Congrout RES is used for precision grouting or for repairs of highways, runways & bridge decks where operation is required with a few hours of placing the material.

Advantages include:

- Hydrogen free gaseous expansion.
- Rapid strength gain.
- Chloride free.
- Excellent durability.
- Excellent flow.
- High strength gain even at low temperatures.
- High ultimate strength.
- Shrinkage compensation in both plastic & hardened state.
- Useable for a wide range of applications and temperatures.
- Flowing grout for gaps 10 mm. to 150 mm.
- No bleeding.
- Non shrink, non toxic and non corrosive.

PROPERTIES

Appearance:	Grey powder
Fresh wet density:	Approx. 2,100 kg./m ³ Depends on consistency
Bond Strength to Concrete:	> 2 N/mm ² at 7 days > 3 N/mm ² at 28 days
Drying Shrinkage: 23°C C/RH 50% ASTM	< 500 micro strain at 28 days
Resistivity:	< 12,000 ohm cm at 28 days

PERFORMANCE PROPERTIES

Water content 11.6% by weight of **Congrout RES**.

Approx. Compressive Strengths at 30°C

Compressive Strength Hours	Typical Results
2 hrs	25-30 N/mm ²
4 hrs	35 N/mm ²
8 hrs	40 N/mm ²
24 hrs	51 N/mm ²
28 days	70 N/mm ²
Expansion :	1.0-2.0%
Working Time :	Approx. 10-12 mins.
Consistency :	Flowable

Note: These are typical figures results may vary depending on water content used, mixing time, and ambient temperatures.

SUBSTRATE PREPARATION

Surface should be clean, sound and free from oil, grease, laitance and loose particles. Metal surfaces should also be clean & free from rust, oil & grease.

Bolt holes or fixing pockets must be cleaned out with blown clean air.

MIXING

Congrout RES should be mixed using a suitable mixer. For flowable consistency use a slow speed < 400 rpm hand drill and paddle. For large works use a high shear vane grout mixer. Drum mixers may not mix sufficiently. For **Congrout RES** use 2.9 litres of clean water for fluid to flowing consistency. Add grout slowly to the water (add the total bag). Mix continuously for 3 minutes ensuring a smooth even consistency is obtained.

APPLICATION

Ensure the substrate is correctly prepared, no contamination and saturated with water at least 3 - 4 hours prior to pouring the grout. No free water should be left. Ensure air entrained into the grout is able to escape. Maintain continuous head when baseplate grouting. Mortar flow should not be interrupted. Formwork should not allow grout loss. Base plates should be clean and free from oil, grease or scale. Air venting holes should be provided to allow venting in isolated spots. Place the grout within 10 minutes of mixing.

CURING

To prevent rapid surface drying and crazing, use a suitable curing compound from Cormix 's **Corcure** range. e.g. **Corcure 90**. At temperatures below 20°C early strength gain maybe affected.

IMPORTANT NOTES

- Minimum applied thickness of **Congrout RES** is 10 mm. maximum 150 mm.
- Bolt holes should be grouted prior to grouting between substrate and base plate.
- Continuous flow should be maintained with a continuous head of grout.
- At temperatures above 35°C - 40°C cooling of water with ice will make handling & placement easier. Mixers & tools should be kept shaded.

CONSUMPTION

Approximate 82-86 bags per m³ of mortar depending on water content used i.e. **Congrout RES** 86 x 25 kg bags and 249.50 litres of water.

CLEANING

Clean all tools with water immediately after use.

PACKAGING

25 kg. 4 Ply plastic lined bags.

RAPID STRENGTH CEMENTITIOUS PRECISION GROUT / MORTAR

STORAGE CONDITIONS & SHELF LIFE

Store in dry shaded conditions. The shelf life is 6 months if kept dry in original packaging. High temperatures and humidity may reduce shelf life.

HEALTH & SAFETY

During use avoid inhalation of dust & contact with skin & eyes. Wear protective clothing. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do **NOT** induce vomiting.

TECHNICAL SERVICE

The Cormix International Limited Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.