

## WATER REDUCING PLASTICISING AND RETARDING CONCRETE ADMIXTURE

### DESCRIPTION

**Conmix P4** is liquid concrete plasticiser and retarder or water reducing agent used to improve the workability of concrete mixes or to allow an effective reduction in free water content to be made. The effect is achieved by its absorption on to the surface of the cement particles in a concrete mix giving a powerful de-flocculating action.

**Conmix P4** is formulated from carefully selected raw materials and is manufactured under controlled conditions to give a consistent product. It is based on a high grade, modified lignosulphonic and carboxylic acid derivative and depending on addition rate conforms to Type A and D materials of ASTM designation C494-81 and with BS5075 : Part 1, GB 8076-1997, BS 5075 Part 1, BS:EN934-2:1998, ASTM C1017 as Type 1 and Type 2.

### USES & ADVANTAGES

**Conmix P4** is used to produce workable and dense concrete in for example, dams, tunnels, runways, canals, reservoirs, ports, and marine structures etc. It is widely used in ready mix & site concrete.

#### Advantages Include:-

- Extension of slump in high temperatures.
- Workability improvement to most types of concrete mixes.
- Increased early compressive & flexural strengths.
- A 10-15% water reducing effect can be obtained.
- Reduced water without loss in workability.
- Can be used for pumped concrete.
- Effective in achieving cement economies.
- Extended setting times in high temperatures.
- Improves surface finishes.

### PROPERTIES

<b>Appearance:</b>	Dark brown liquid
<b>Specific Gravity:</b>	Approx. 1.23
<b>Air Entrainment:</b>	1 - 2 %
<b>pH Value:</b>	Approx. 5
<b>Chloride Content:</b>	Nil

#### Compatibility with Cements:

**Conmix P4** can be used with all types of Portland Cement, concrete containing fly ash, silica fume or G.G.B.F.S. For use with special cements we recommend that you consult Cormix.

#### Compatibility with Other Admixtures:

**Conmix P4** should not be premixed with other admixtures. The performance of the material may be affected by the presence of other chemicals and we would recommend that Cormix International be consulted in such circumstances.

### METHOD OF USE / APPLICATION

**Conmix P4** is supplied ready for use, it should be added to concrete mixes during the mixing process at the same time as the water or the aggregates. It should not be added directly to the cement. No extension of normal mixing time is necessary.

### DOSAGE

The performance of **Conmix P4** is best assessed after preliminary tests on site using the actual concrete under consideration to determine the optimum dosage and effect on properties such as compressive strength, setting times, shrinkage etc., when these are of consequence. As a guide to these trials, an addition rate of 0.2-0.5% by weight of cement, is recommended. This rate of addition can be varied to give different results. For advice and assistance with your trials we would recommend that you consult Cormix.

### EFFECTS OF OVER-DOSING

Over-dosing of **Conmix P4** will cause an extension of initial setting time. If this happens consult Cormix.

If intentional or accidental increases above the recommended addition rate are employed, care must be taken to allow for the effect on the stripping of formwork. In such cases, however, provided the concrete is properly cured, the ultimate strength will generally be higher than for normal concrete.

### PACKAGING

**Conmix P4** is supplied in 200 litre steel drums. Alternatively bulk deliveries can be arranged.

### STORAGE & SHELF LIFE

**Conmix P4** should be protected from frost. If frozen remix on thawing. Storage under high temperatures causes no adverse effect. The shelf life is a minimum of 12 months in original packaging.

### HEALTH & SAFETY

**Conmix P4** is formulated from chemicals which present no fire or health hazards. Do not take internally. If on skin wash off with soap and water. If in eyes wash out with copious amounts of water and seek medical attention. For further information consult Cormix's MSDS.

### TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

### QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

### CONTACT DETAILS

#### Cormix International Limited

Regional Office,  
89 Romkiao Rd., Sansab, Minburi, Bangkok 10510  
Tel. (66 2) 917 3955-8, 543 8890  
Fax. (66 2) 917 3959, 543 8891  
<http://www.cormix.com> E-mail : [info@cormix.com](mailto:info@cormix.com)

Rev. 012 : Jun 2010

**NOTE :** Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.