

HIGH RANGE WATER REDUCING SUPERPLASTICISER

DESCRIPTION

Conmix SP1C is a highly effective water reducing superplasticiser and an extremely powerful deflocculating agent, it operates by dispersing cement in to its primary particles which dramatically increases the flow characteristics of the cement paste. Based on the soluble salt of a polymeric sulphonate it conforms to Type A and F materials of ASTM C494 and BSEN 934-2 1998.

USES & ADVANTAGES

Uses include to produce flowing concrete for large pours and precast elements. **Conmix SP1C** may also be used where substantial water reductions are required to provide high early and ultimate strengths e.g. in precast factories.

Advantages include:-

- High strength concrete produced at normal workability and cement contents. The resultant concrete is of a dense impermeable nature.
- Substantial increase in workability without additional water.
- Normal setting without retardation.
- Very good early strengths.
- Significant strength increases.
- Increased productivity in precast yards.
- Better surface finish.
- Waterproof concrete may be achieved.
- Better resistance to wear & abrasion.
- Chloride free.
- Reduced shrinkage & creep.
- Suitable for hot climates.
- Improved water borne salt resistance.

PROPERTIES

Appearance: Brown liquid

Chemical: Napthalene Formaldehyde Sulphonate

Specific Gravity: 1.14 ± 0.01 at 25°C

pH Value: 8-10

Chloride Content: Nil

Compatibility with Cements:

Conmix SP1C can be used with all types of Portland Cement and pozzolanic materials.

Conmix SP1C is compatible with P.F.A., G.G.B.F.S. and Silica fume. For use with special cements we recommend that you consult Cormix International Ltd.

Compatibility with Other Admixtures:

Conmix SP1C should not be premixed with other admixtures. Consult Cormix when using other admixtures.

METHOD OF USE / APPLICATION

Conmix SP1C is supplied ready for use, it should be added to concrete mixes during the mixing process at the same time as the water or the aggregates. It should not be added directly to the cement.

DOSAGE

0.5 - 3.0% by weight of cement.

Exact dosage rates should be determined by trial mixes.

EFFECTS OF OVER-DOSING

Over-dosing of **Conmix SP1C** will generally produce a considerable increase in workability. Providing over dosed concrete is properly cured the ultimate strength will generally be higher than of a normal concrete.

PACKAGING

Conmix SP1C is supplied in 200 litre steel drums. Alternatively bulk deliveries can be arranged.

STORAGE & SHELF LIFE

Conmix SP1C should preferably be stored protected from frost. If the product does become frozen it should be carefully mixed after thawing out, to restore it to its normal state.

Conmix SP1C can also be stored under high, ambient temperatures, without any adverse effect on its performance. The shelf life is at least 12 months when stored in original unopened containers.

HEALTH & SAFETY

Conmix SP1C is formulated from chemicals which present no fire or health hazards.

Do not take internally. If on skin wash off with soap and water. If in eyes wash out with copious amounts of water and seek medical attention.

For further information consult Cormix International Ltd.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

Regional Office,

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com> E-mail : info@cormix.com

Rev. 002 : Jun 2010

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out that oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.