

Contite[®] Waterstop Delay Coating

DELAY COATING FOR HYDROPHILIC CONSTRUCTION JOINT WATERSTOP

DESCRIPTION

Contite Waterstop Delay Coating is a water based protective delay coating used to stop the premature swelling of **Contite Waterstop** in wet conditions.

USES

Contite Waterstop Delay Coating is used to delay swelling of **Contite Waterstop** for several days in wet conditions.

TYPICAL PROPERTIES

Appearance :	Milky white
S.G. :	0.93-0.96
p H :	9-11
Total Solid Content :	60.0-65.0

Day	Swell rate (% by volume)	
	With Delay Coating	Control (Without delay coating)
1	No swelling	200%
2	No swelling	255%
3	118%	306%
4	130%	365%
5	143%	500%

INSTALLATION

After installation of **Contite Waterstop**, spray or brush **Contite Waterstop Delay Coating** on 3 sides with a minimum of 0.1 mm. thickness. Allow **Contite Waterstop Delay Coating** to dry for 30 minutes.

COVERAGE RATE

Application Rate: 1 litre per 10-12 LM at 0.1 mm. thick.

LIMITATIONS

Contite Waterstop surface should be clean and dry.
Do not allow to freeze prior to use.

PACKAGING

5 litre plastic pails.

STORAGE & SHELF LIFE

Contite Waterstop Delay Coating should be stored protected from sunlight and frost. The shelf life is at least 6 months in original unopened containers.

HEALTH & SAFETY

There are no known hazards associated with **Contite Waterstop** during normal use. Refer to product material safety data sheet.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2008 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com>

E-mail: info@cormix.com

Rev.004 Nov 2014