

Contite® PUE 500/501

2 PART RIGID POLYURETHANE FOAM FOR SOIL & ROCK CONSOLIDATION AND BELOW GRADE WATER STOPPAGE

DESCRIPTION

A new generation phthalate free high performance low viscosity hydrophobic rigid polyurethane injection grout used to increase the load bearing capacity of loose soils, void filling or underpinning. **Contite PUE 500/501** reacts into either a hard foam or very hard plastic. Reaction times may be adjusted by varying the **Contite PUE 500/501** ratio. **Contite PUE 500/501** does not foam on its own, it needs water present to foam.

USES & ADVANTAGES

Contite PUE 500/501 may be used for soil and rock consolidation, filling of large voids, cracks and crevices, pre injection for waterproofing and consolidation in front of TBM and drill and blast, filling of fissures, gravel layers, in wet and dry conditions.

Advantages Include:-

- Phthalates free resins.
- Solvent free.
- Fast or slow reactions available.
- Easy mixing 1:1 by volume.
- Can be applied in dry or wet conditions.
- Environmentally friendly.
- Expands 20-30 times.
- High strength.
- Non shrink.
- Bonds with soil and concrete.
- Stops repeated water erosion.
- Suitable for long distance injection.

PROPERTIES

	For Part A	For Part B
Appearance:	Yellow	Dark brown
Viscosity: (mPa.s)@25°C	70-120	170-270
SG:	1.04-1.06	1.22-1.25
pH Value:	5.5-6.5	7.0-8.0

	Mixed Material
Appearance:	Light brown
Viscosity:	100-200
Density:	1.13-1.16
pH Value:	6.0-7.0

	Foam Properties
Pot Life:	5 minutes
Reaction Time:	20-30 seconds
Expansion Time:	Approx. 5 minutes
Compressive Strength:	> 40 N/mm ² at 7 days
ASTM C579	(with fine sand)
Tensile Strength:	1.5 MPa
ASTM D638	

Young's Strength:	50 MPa
ASTM D638	
(Contite PUE 500/501) + 1% water :	Rigid Foam (Less Expansion)
(Contite PUE 500/501) + 5% water :	Less Rigid Foam (More Expansion)

MIX RATIO

Contite PUE 500 : Contite PU 501 = 1:1 by volume

APPLICATION

- **Contite PUE500/501** is injected using a 2 component injection machine such as GRACO REACTOR E-30 (plural component proportioner) where the two hoses are connected with an injection gun before injecting into the drilled holes.
- Clean and flush all equipment with **Contite PU Purge** prior to the injection.
- Check the mixing ratio of **Contite PUE 500** and **Contite PU 501** at the GRACO REACTOR by injecting the Part A & Part B under pressure initially, to ensure this is 1:1 mix ratio by volume.
- Fill the machine & hoses with **Contite PUE 500** Part A and **Contite PU 501** Part B and first flush the liquid into waste drums until fresh liquid is observed from the hoses.
- Insert the injection head into the drilled holes.
- Adjust pressure at the GRACO Reactor for Part A and Part B and start the injection, so as to achieve 1:1 mix ratio by volume.
- The injection should be continued until the water flow stops, or until the pre-measured amount of product has been injected in each drilled hole.
- After injecting into the first hole, remove the injection gun & start injecting into adjacent drilled hole situated at 30 cm interval from the previous drilled holes.
- Continue and repeat the injection steps with the adjacent drilled hole.
- When the injection has finished, clean and rinse all equipment with **Contite PU Purge**.
- All opened drums should be capped when not in use.

PACKAGING

400 litres set; available in **Contite PUE 500** 200 litres & **Contite PU 501** 200 litres in 200 litres steel drums. Other packing units are available on request.

STORAGE CONDITIONS & SHELF LIFE

Store in the shade in dry conditions. Stored in unopened sealed drums, in a dry area, at temperatures of 5°C-35°C, the shelf life is approximately 12 months.

HEALTH & SAFETY

Avoid skin and eye contact. Wear rubber gloves and safety goggles. Hands should be cleaned with cleaner, followed by soap and water. Avoid breathing of vapours; use with adequate ventilation. Please consult our MSDS for more information (available upon request).

Contite® PUE 500/501**2 PART RIGID POLYURETHANE FOAM FOR SOIL & ROCK CONSOLIDATION AND BELOW GRADE WATER STOPPAGE****TECHNICAL SERVICE**

The Cormix International Limited Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001: 2008 verified by TUV Nord.



Cormix International Limited 89 Romklao Rd, Sansab, Minburi, Bangkok 10150 09 1012-CPD-0105 EN 1504-5	Water tightness :	2x10 ⁵ Pa 7x10 ⁵ Pa
	Corrosion behavior :	Deemed to have No corrosive Effect
Concrete Injection : Injection Products for Expansive Filling of Cracks, Voids and Interstices in Concrete U(S1)(S2)(S3)W(2)(3/4)(5/35)(0)	Workability :	Degree of crack filling : > 95% Moisture state of crack: Wet, Running water
	Suitable for use :	5°C to 35°C
	Sensitivity to Water :	Expansion rate is Constant when Immersed in water

CONTACT DETAILS

Cormix International Limited
89 Romklao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8, 543 8890
Fax. (66 2) 917 3959, 543 8891
<http://www.cormix.com>
E-mail : info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out those oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.