

Conflex® Cell

NON ABSORBENT, CLOSED CELL POLYETHYLENE JOINT FILLER

DESCRIPTION

Conflex Cell is a non-absorbent, rot proof, closed cell polyethylene joint filler which is semi rigid and particularly suitable to from expansion joints in brickwork, blockwork and concrete.

USES & ADVANTAGES

Conflex Cell may be used as back up & bond breaker to support sealants and forming or filling expansion joints e.g. in bridge decks, parapets, abutments, subways, sewage treatment works, raw & potable water reservoirs, irrigation channels & culverts, brick & blockwork in building superstructures, water retaining structures, traffic joints in chemical plants, road joints, joints in chemical banded areas.

Advantages include:-

- Bitumen free.
- C.F.C free.
- Rot proof.
- Non absorbent. Non tainting.
- Does not expand where in contact with water.
- Does not damage joint sealant.
- Resilient.
- Excellent recovery after compression.
- Easily cut on site to size required.
- Low load transfer.
- Readily compressible.
- Excellent chemical resistance.
- Particularly recommended for storage of potable water.

PROPERTIES

Form:	Semi rigid closed cell heat laminated sheet.	
	Grey colour.	
Density:	50 kgs/m ³	
Thermal Conductivity: (ASTM C177-97)	0.022 W/mK at 17.5°C	
Water Absorption:	0%	
Flammability:	HF-2	
Compressive Strength:	1.7 N/CM ²	@10 %
	3.4 N/CM ²	@25 %
	8.9 N/CM ²	@50 %
Elongation		
First Direction:	94.70 %	
Second Direction:	107.10 %	
Tensile Strength		
First Direction:	36.7 N/CM ²	
Second Direction:	69.7 N/CM ²	
Tearing Strength:	35.6 N/CM ²	
UV Resistance:	Excellent with paint	
Chemical Resistance: (ASTM D1308)	No change	

APPLICATION

When installed in expansion joints between suspended slabs copper nails or adhesive may be used to hold in place. **Conflex Cell** is particularly suitable for expansion joints between bricks.

Joint sealing slots can be easily formed by cutting off a strip to the required depth. Put the strip back by fixing with 5 cm. nails at intervals. Install the filler flush with the finished surface. Before sealing the top strip can be easily removed leaving a clean, ready to fill slot. Bond breakers are not required with **Conflex Cell** as elastomeric sealants will not bond to it.

IMPORTANT NOTES

Unlike fibre boards **Conflex Cell** does not damage elastomeric sealants. In general bitumen impregnated fibre boards should not be used with elastomeric sealants as mobile fractions attack & damage the sealant. Use **Conflex Cell** in conjunction with **Conflex** elastomeric joint sealants. Bitumen fibre boards tend to absorb water & expand **Conflex Cell** does not absorb water

CONSUMPTION

Conflex Cell is supplied in sheets which can easily be cut to size with a knife or saw.

Sheet width: 0.6 m.

Sheet Thickness: 10, 15, 20, 25 mm.

Conflex Cell can be cut to order. Other thickness available.

STORAGE & SHELF LIFE

Store in clean area. In hot climates it is preferable not to leave exposed for long periods. Shelf life is indefinite.

HEALTH & SAFETY

There are no health hazards associated with **Conflex Cell** in normal use.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2015 verified by TUV Nord.

CONTACT DETAILS

Cormix International Limited

89 Romklat Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8, 543 8890

Fax. (66 2) 917 3959, 543 8891

<http://www.cormix.com>

E-mail: info@cormix.com

Rev.011 Oct 2018

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out those oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.