

Condur® Rail Fix

POLYURETHANE ELASTOMERIC GROUT

DESCRIPTION

Condur Rail Fix is an elastomeric polyurethane rail grout providing vibration, dampening and electrical isolation whilst holding the rail securely in place absorbing movement without cracking. It is very rapid setting and may be used in new and repair applications. The product is in two parts to control the finished materials consistency, there is no need to add further aggregates.

USES & ADVANTAGES

Condur Rail Fix grout is used for filling the space between the rail and adjacent concrete. It is used with longitudinal rail and floating slab joints and embedded rails. Use for rail maintenance and new construction.

Advantages include:-

- Fast setting and curing.
- · Setting time may be adjusted.
- · Noise reduction.
- · Electrical isolation.
- Bonds tenaciously to steel and concrete.
- Chemical, oil and fuel resistant.
- No VOCs.
- Self priming
- Flexible.
- Flowable.
- · Easy to mix.
- Two part providing better quality control.

PROPERTIES

Specific Gravity @25°C: 1.10 -1.16 kg/litre
Final Setting Time @25°C: Approx. 60 min.
Volume Resistivity: 3.46 x 10¹² ohm.m.

ASTM D257

Tensile Strength: ≥ 2 MPa.

ASTM D638

Elongation at Break : \geq 100 %

ASTM D638

Shore A Hardness : ≥ 50

(Full Cure) ASTM D2240

Impact Resistance: No crack or breaks

ASTM D3029 observed.

Trafficable at 25°C: Approx. 2 hours.

Full Cure Time at 25°C: 7 Days

Adhesion Bond Strength: >2 N/mm²
to Concrete @ 7 Days (Concrete failure)

ASTM D4541

Service Temperature : - 40 to 80°C

Chemical Resistance:

ASTM D543

Dilute sulphuric acid & NaOH solution Sea, Chlorine and Waste water

Glycerine Soap solution Fuels & oils

Note: For more information details on chemical resistance contact Cormix International Limited.

Note: Condur Rail Fix is moisture sensitive.

Protect from rain until it has reached its final setting time.

Do not apply the product below 7°C. Temperature should be 7°C & rising.

Wet & damp conditions: prime with Condur EA1.

PERFORMANCE PROPERTIES

It is very important to compare the data of the fully mixed material.

To ensure performance is maintained **Condur Rail Fix** is supplied in two parts in pre measured units.

CONSUMPTION

Approx. 92-97 sets of **Condur Rail Fix** will yield 1 cubic metre of elastomeric grout.

SUBSTRATE PREPARATION

Ensure no moisture is present in the substrate. Hot air blasting can be used to remove excess moisture from the substrate. In the case of repairs cut out all damaged spalled concrete to leave a clean, dust free, dry, exposed aggregate surface, ensure there is no contamination. The edges of the repair must be cut at right angles the full depth of the repair. New concrete should be at least 14 days old, clean, free of contaminants such as oil, grease, curing compound or other materials that interfere with adhesion. No primer is required when the concrete surface is prepared clean and roughened.

In the case where additional bonding to the substrate is required, primer is available upon request.

For wet & damp conditions prime with **Condur EA1.** Allow to dry for approx. 30 minutes to 2 hrs.

MIXING & APPLICATION

STEP-1: MIXING PART A & B

Mix "Part A" & "Part B" for approx. 2-3 minutes using a high speed drill mixer (or) paddle mixer having ribbon blades until a uniform homogenous mixture is achieved.

STEP-2: PLACING OF CONDUR RAIL FIX

Pour the homogenous mixture of **Condur Rail Fix**, immediately into the prepared area.

The poured material is self levelling.

STEP-3: CURING & FINISHING

The poured material will initially cure within 10-20 minutes, providing a smooth surface finish.

The applied product can accept traffic in approx. 2 hours.

CLEAN UP

Use xylene to clean equipment.

PACKAGING

12 kg set.

12 kg set = 10.6 litres.



Condur® Rail Fix

POLYURETHANE ELASTOMERIC GROUT

STORAGE & SHELF LIFE

Do not allow to freeze. Store in a dry shaded area between 10-35 °C in original unopened containers. The shelf life is 12 months when stored correctly in the original unopened containers.

HEALTH & SAFETY

Wear protective clothing, goggles & gloves. If in contact with eyes wash out immediately with water & seek medical attention.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2015 verified by TUV Nord. ISO 14001 : 2015 verified by Lloyd's Register International.

DISCLAIMER

Performance data is achieved testing in accordance with International Standards. Testing by others may result in different results from those published as a result of external factors such as poor sampling, incorrect mixing, varying temperatures, curing, crushing procedures etc. Cormix does not take responsibility nor need to defend others testing that does not achieve the published data. The user must test the products suitability for the intended application and purpose. Cormix reserves the right to change the properties of the product. Site conditions and differences in materials are such that no warranty or fitness for a particular purpose, nor liability can be inferred from the published data sheet, written recommendations or from other advise offered.

CONTACT DETAILS

Cormix International Limited

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8

Fax. (66 2) 917 3959, 543 8891

http://www.cormix.com E-mail: info@cormix.com