

Cormix® SP1A

HIGH RANGE WATER REDUCING SUPERPLASTICISER WITH HIGH EARLY STRENGTH PROPERTIES

DESCRIPTION

Cormix SP1A is a highly effective water reducing superplasticizer, an extremely powerful defloculating agent, it operates by dispersing cement in to its primary particles which dramatically increases the flow characteristics of the cement paste. Based on the soluble salt of a polymeric sulphonate it conforms to Type A and F materials of ASTM C494 and EN 934-2 Table 7

USES & ADVANTAGES

Cormix SP1A may be used to produce flowing concrete with high early & ultimate strengths or in the production of precast concrete that requires substantial water reductions and very high early strengths.

Advantages include:-

- High strength concrete produced at normal workability and cement contents. The resultant concrete is of a dense impermeable nature.
- Substantial increase in workability without additional water.
- Normal setting without retardation.
- Very high early strengths.
- Significant strength increases.
- Increased production rates in precast yards.
- Better surface finish.
- Waterproof concrete may be achieved.
- Better resistance to wear & abrasion.
- Chloride free.
- Reduced shrinkage & creep.
- Suitable for hot climates.
- Improved water borne salt resistance.
- Substantial cement reductions due to accelerated early strengths.

PROPERTIES

Appearance: Brown liquid

Chemical: Naphthalene Formaldehyde Sulphonate

Specific Gravity: 1.18 - 1.20 approx. at 20°C

pH Value: 7-9

Chloride Content: Nil

Compatibility with Cements:

Cormix SP1A can be used with all types of Portland Cement and pozzolanic materials.

Cormix SP1A is compatible with P.F.A., G.G.B.F.S. and Silica fume. For use with special cements we recommend that you consult Cormix International Ltd.

Compatibility with Other Admixtures:

Cormix SP1A should not be premixed with other admixtures. Consult Cormix when using other admixtures.

METHOD OF USE / APPLICATION

Cormix SP1A is supplied ready for use, it should be added to concrete mixes during the mixing process at the same time as the water or the aggregates. It should not be added directly to the cement.

DOSAGE

1.0-3.0 litre per 100 kg of total cementitious material. Exact dosage rates should be determined by trial mixes.

EFFECTS OF OVER-DOSING

Over-dosing of **Cormix SP1A** will generally produce a considerable increase in workability. Providing over dosed concrete is properly cured the ultimate strength will generally be higher than of a normal concrete.

PACKAGING

Cormix SP1A is supplied in 200 litre steel drums. Alternatively bulk deliveries can be arranged.

STORAGE & SHELF LIFE

Cormix SP1A should preferably be stored protected from frost. If the product does become frozen it should be carefully mixed after thawing out, to restore it to its normal state.

Cormix SP1A can also be stored under high, ambient temperatures, without any adverse effect on its performance.

The shelf life is at least 12 months when stored in original unopened containers.

HEALTH & SAFETY

Cormix SP1A is formulated from chemicals which present no fire or health hazards.

Do not take internally. If on skin wash off with soap and water. If in eyes wash out with copious amounts of water and seek medical attention.

For further information consult Cormix International Ltd.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

Cormix® SP1A**HIGH RANGE WATER REDUCING SUPERPLASTICISER WITH HIGH EARLY STRENGTH PROPERTIES****QUALITY ASSURANCE**

ISO 9001 : 2015 verified by TUV Nord.
ISO 14001 : 2015 verified by Lloyd's Register International.

DISCLAIMER

Performance data is achieved testing in accordance with International Standards. Testing by others may result in different results from those published as a result of external factors such as poor sampling, incorrect mixing, varying temperatures, curing, crushing procedures etc.

Cormix does not take responsibility nor need to defend others testing that does not achieve the published data.

The user must test the products suitability for the intended application and purpose. Cormix reserves the right to change the properties of the product. Site conditions and differences in materials are such that no warranty or fitness for a particular purpose, nor liability can be inferred from the published data sheet, written recommendations or from other advise offered.

CONTACT DETAILS

Cormix International Limited
89 Romklao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8
Fax. (66 2) 917 3959
<http://www.cormix.com>
E-mail: info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available, and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out those oral recommendations, which vary from the instructions contained herein, is not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.