

Congrout® AF

A PREMIXED CEMENTITIOUS CABLE GROUT

DESCRIPTION

A ready to use high strength premixed flowing non shrink cable grout. Expansion/no shrinkage ensures good interfacial contact is maintained. **Congrout AF** complies to BS EN 447.

USES & ADVANTAGES

Use for the grouting of prestressed cable ducts, bearing plates, tunnel linings, rock & soil anchoring etc.

Advantages include:-

- Flows with low water cement ratio.
- Reduced bleeding.
- Ready to use.
- Non shrink.
- Good expansion.
- Good strength & adhesion.
- Prolonged workability.
- Both non hydrogen & hydrogen forming available.

PROPERTIES

Appearance:	Grey powder
Density of Freshly Mixed Grout	Approx. 2 kg/l
Shrinkage:	Nil
Chloride Content %:	Nil
Typical Strengths:	

	Flexural Strength ASTM C348	Compressive Strength ASTM C109
24 hours	2 N/mm ²	≥25 N/mm ²
3 Days	3 N/mm ²	≥30 N/mm ²
7 Days	4 N/mm ²	≥37 N/mm ²
28 Days	5 N/mm ²	≥48 N/mm ²

Flow : Flowing at water cement ratio of 0.35-0.40 J-rote <3 seconds over 2 hours ASTM marsh cone 18 seconds over 2 hours at 0.4 w/c. Flow is effected by temperature and water contents.

Expansion: According to ASTM C-827 an unrestrained expansion of 1-4% is typical. Expansion is effected by temperature and water contents.
Note: In the non-hydrogen forming material expansion is negligible.

Bleeding: Typically Less than 2% at 3 hours and reabsorption within 24 hours according to ASTM C232.

Workability: 90-120 minutes depending on temperature.

Retention & W/C

Curing: Cure cubes in plastic bags not water.

Shrinkage: None

SURFACE PREPARATION

Surfaces should be clean, sound and free from oil, grease, laitance and loose particles. Metal surfaces should also be clean & free from rust, oil & grease.

MIXING & APPLICATION

Mixing times and w/c vary according to the application. With standard mechanical mixing for prestressed concrete work, a mixing time of 4 minutes with a w/c of 0.35-0.40 gives the best results.

The best mixing sequence is normally water : **Congrout AF**. Ensure the substrate is correctly prepared. During application ensure trapped air and air entrained into the grout is able to escape through relief holes. Maintain continuous head when grouting. Mortar flow should not be interrupted.

IMPORTANT NOTES

Congrout AF is generally used in the highly specialized work of grouting and prestressing. Properties of **Congrout AF** may be influenced by mixing procedure, adding of water and temperatures. Therefore tests on site should be undertaken.

CLEANING

Clean all tools with water immediately after use.

PACKAGING

20 kg. 4 ply plastic lined bags.

STORAGE & SHELF LIFE

Store in dry shaded conditions. The shelf life is 6-9 months if kept dry in original packaging. High temperatures and humidity may reduce shelf life.

HEALTH & SAFETY

Congrout AF is alkaline avoid contact with skin & eyes. Gloves, goggles and dust mask should be worn. Remove from skin with soapy water. Splashes in the eyes should be washed out with copious amounts of clean water and medical attention sought.

Congrout AF is non-flammable.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2015 verified by TUV Nord.
ISO 14001 : 2015 verified by Lloyd's Register International.

CONTACT DETAILS

Cormix International Limited

89 Romklat Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8

Website: <http://www.cormix.com>

Email Address: info@cormix.com